



CLICK HERE
To view stock levels
and colours
on our product
pages




Technical Xtreme Outdoor Fabrics by
Bainbridge




- ◆ Fabric width: 1.94m
- ◆ PU coated with Fluorocarbon+ finish
- ◆ Solution dyed polyester
- ◆ >1000mm hydrostatic water column*



Black - F82519499




White - F82519400



Cadet Grey - F82519494



Charcoal Grey - F82519492



Silver - F82519490



Ivory - F82519402



Sahara - F82519432



Beige - F82519423



True Red - F82519410



Pacific Blue - F82519460



Navy Blue - F82519462



Forest Green - F82519450


Exceeding the highest requirements for functionality and lifespan



SolaTX Benefits

25% BETTER
than the nearest competitor
in its field*

- ◆ Technical ribbed ottoman weave
- ◆ Low weight
- ◆ High breathability
- ◆ Water tightness
- ◆ PVC free
- ◆ High UV resistance
- ◆ No colour bleed or rub-off
- ◆ Superb colour fastness
- ◆ Xtreme strength and tear resistance
- ◆ Salt water, oil, dirt and water repellent
- ◆ Flame resistant with an antimicrobial finish
- ◆ Easy handling for storage
- ◆ Fluoro+ finish for dirt and water repellency
- ◆ Mould resistant
- ◆ No stress whitening
- ◆ Dimensionally stable



SolaTX Polyester Technical Data

| Testing | Typical Value | Testing Methods |
|------------------|---|-------------------------|
| Material Base | 350 dtex Polyester, PU-coating and Fluoro+ finish | - |
| Roll Width | 1.94m | - |
| Roll Length | 50m | - |
| Weight | 280gsm | ISO 3801-1977, Method 5 |
| Colour Fastness | 7 Level | DIN EN ISO 105 B02 |
| Tensile Strength | Warp >1500N / 5cm, Weft >1300N / 5cm | DIN EN ISO 13934-1 |
| Elongation | Warp 45%, Weft 30% | DIN EN ISO 13934-1 |
| Tear Strength | Warp >40N, Weft >40N | DIN EN ISO 13937-2 |
| Water Column | >1000mm | ISO 811 |
| UPF | 50+ | - |
| UV-Stability | >4 - 5 | ISO 4892-2 after 2000 h |
| Flame Resistance | Self-Extinguishing | FMVSS 302 |

CARE & CLEANING

Proper care and cleaning should be taken to ensure the life of **SolaTX** fabrics.

For regular care and maintenance, the excess dirt should be brushed from the fabric using a soft brush: the fabric should then be sprayed with warm water and air dried.

Periodically, the fabric should undergo a more thorough cleaning. Again, brush the fabric with a soft bristled brush, spray with warm water, then apply a gentle soap. Allow to stand for 10-20 minutes taking care not to let it dry, then rinse thoroughly and air dry.

Do not use detergents and /or solvents.

WARRANTY

SolaTX fabrics are manufactured with only the highest quality raw materials and the most rigorous quality-assurance procedures in Europe. We offer a 5 year limited warranty on our **SolaTX** solution dyed polyester products.



The technical data is to be considered as indicative.
Minor colour variations possible between batches. Ensure only one batch is used per order.
Can be sewn or ultra-sonically welded.



Bainbridge International Ltd

8 Flanders Park, Southampton, Hampshire SO30 2FZ UK

T: +44 (0) 1489 776000

E: info@bainbridgeint.co.uk

W: bainbridgeint.com